PCN Number: 2022			2081	7001.1		PC	CN Date: August 18, 2			
I ITIA'			w Fa	b site (FFAB) using o	jualified Pro	cess	Technolo	gy, Die Revision,		
			and	additional Assembly	site for sele	ect de	evices			
Cus	tomer	Contact:	<u>F</u>	PCN I	<u>Manager</u>	Dept:		Qua	Quality Services	
Proposed 1 st Ship Date:			Nov 1	.8, 2022	Sample reaccepted	-		Sep 18, 2022*		
*Sample requests received			after September 18, 2022 will not be sup		e support	ted.				
Change Type:										
\boxtimes	Assen	nbly Site			Assembly Process		\boxtimes	Assembl	y Materials	
\boxtimes	Desig	n						Mechanical Specification		
	Test S	Site			Packing/Shipping/L	abeling		Test Process		
	Wafer	Bump Site			Wafer Bump Material			Wafer Bump Process		
\boxtimes	Wafer	Fab Site		\boxtimes	Wafer Fab Material	S	\boxtimes	Wafer Fab Process		
				Part number chang	je					
					PCN Detai	ils		·		
		4.01								

Description of Change:

Texas Instruments is pleased to announce the qualification of a new fab & process technology (FFAB, BICOMHD) and additional Assembly site (HFTF) for selected devices as listed below in the product affected section.

С	urrent Fab Site)	A	dditional Fab S	ite
Current Fab Site	Process	Wafer Diameter	Additional Fab Site	Process	Wafer Diameter
DL-LIN	BICOM	150 mm	FFAB	BICOMHD	200 mm

The die was also changed as a result of the process change.

Construction differences are noted below:

	HANA	HFTF			
Mount compound	400154	A-18			
Mold Compound	450179	R-30			
Wire type	1.0 mil Au	1.0 mil Cu			
Lead finish	Non-roughened NiPdAu	Roughened NiPdAu			

The datasheet will be changing as a result of the above mentioned changes. The datasheet change details can be reviewed in the datasheet revision history. The link to the revised datasheet is available in the table below.



THS4130, THS4131

SLOS318K - MAY 2000 - REVISED AUGUST 2022

_		
С	hanges from Revision J (March 2022) to Revision K (August 2022)	Page
:	Updated thermal specifications for DGK package in <i>Thermal Information</i> table	
•	Changed title of Electrical Characteristics: THS413xDGK, THS413xDGN table to Electrical Characteristi THS413xDGN	
:	Changed title of <i>Typical Characteristics: THS413xD</i> to <i>Typical Characteristics: THS413xD</i> , <i>THS413xDG</i> . Changed title of <i>Typical Characteristics</i> to <i>Typical Characteristics: THS413xDGN</i>	K 11

Product Family	Current Datasheet Number	New Datasheet Number	Link to full datasheet
THS413x	SLOS318J	SLOS318K	https://www.ti.com/product/THS4130

Tube versions of the devices are included in EOL notice PDN# 20220817002.3

Qual details are provided in the Qual Data Section.

Reason for Change:

These changes are part of our multiyear plan to transition products from our 150-milimeter factories to newer, more efficient manufacturing processes and technologies, underscoring our commitment to product longevity and supply continuity.

Anticipated impact on Form, Fit, Function, Quality or Reliability (positive / negative):

None

Impact on Environmental Ratings

Checked boxes indicate the status of environmental ratings following implementation of this change. If below boxes are checked, there are no changes to the associated environmental ratings.

RoHS	REACH	Green Status	IEC 62474
☑ No Change	☑ No Change	☑ No Change	⊠ No Change

Changes to product identification resulting from this PCN:

Fab Site Information:

Chip Site	Chip Site Origin Code (20L)	Chip Site Country Code (21L)	Chip Site City
DL-LIN	DLN	USA	Dallas
FR-BIP-1	TID	DEU	Freising


Die Rev:

Current	New
Die Rev [2P]	Die Rev [2P]
Α	A

Assembly Site Information:

Assembly Site	Assembly Site Origin (22L)	Assembly Country Code (23L)	Assembly City
Hana Semiconductor	HNT	THA	Ayutthaya
Hefei Tongfu Microelectronics Co. Ltd.	HFT	CHN	Hefei

Sample product shipping label (not actual product label)



(1P) \$N74L\$07N\$R (Q) 2000 (D) 0336 (31T)LOT: 3959047MLA (4W) TKY(1T) 7523483\$12 (P) (2P) REV: (V) 0033317 (201) C60: SHE (21L) CCO: USA (22L) ASO: MLA (23L) ACO: MYS

Product Affected:

Group 1 Device list (Wafer fab, die revision, Assembly site/BOM and Datasheet)

THS4130IDGKR THS4131CDGKR THS4131IDGKR	KR THS4131CD	GKR THS4131ID	GKR
--	--------------	---------------	-----

Group 2 Device list (Datasheet changes o	nly)
THS4130CDGK	THS4131CDGK	THS4131IDGK
THS4130IDGK	THS4131CDGKG4	THS4131IDGKG4

For alternate parts with similar or improved performance, please visit the product page on $\overline{\text{TI.com}}$

Qualification Report

Approve Date 11-May-2022

Qualification Results Data Displayed as: Number of lots / Total sample size / Total failed

Ту	pe Test Name / Condition	Duration	Qual Device: <u>THS4130DGK</u>	QBS Product Reference: <u>THS4130ID</u>	QBS Process Reference: <u>OPA2810IDGK</u>	QBS Package Reference: <u>OPA2607QDGKRQ1</u>	QBS Package Reference: <u>OPA2991QDGKRQ1</u>
нт	OL Life Test, 125C	1000 Hours	-	-	3/231/0	-	-
Н	OL Life Test, 150C	408 Hours	-	-	-	1/77/0	3/231/1 (1)
EL	FR Early Life Failure Rate, 125C	48 Hours	-	-	3/3000/0	-	-
н	BM ESD - HBM	2500 V	-	1/3/0	3/9/0	1/3/0	-
CI	DM ESD - CDM	1000 V	1/3/0	1/3/0	3/9/0	1/3/0	-
CI	DM ESD - CDM	1500 V	1/3/0	1/3/0	3/9/0	1/3/0	-
L	U Latch-up	Per JESD78	-	1/6/0	3/18/0	-	-
E	D Electrical Characterization	Per Datasheet Parameters	-	1/30/0	3/90/0	-	-
A	C Autoclave 121C	96 Hours	-	-	-	-	3/231/0
HA	ST Biased HAST, 130C/85%RH	96 Hours	-	•	3/231/0	1/77/0	3/231/2 (1)
н	SL High Temp Storage Bake 150C	1000 Hours	-	-	-	1/77/0	2/90/0
н	SL High Temp Storage Bake 170C	420 Hours	-	•	3/231/0	-	-
UH	AST Unbiased HAST 130C/85%RH	96 Hours	1/77/0	-	3/231/0	1/77/0	-
Т	C Temperature Cycle, - 65/150C	500 Cycles	1/77/0		3/231/0	-	3/231/1
	.l Lead Pull	Lead Pull	-	•	-	1/6/0	-

Туре	Test Name / Condition	Duration	Qual Device: <u>THS4130DGK</u>	QBS Product Reference: <u>THS4130ID</u>	QBS Process Reference: <u>OPA2810IDGK</u>	QBS Package Reference: <u>OPA2607QDGKRQ1</u>	QBS Package Reference: <u>OPA2991QDGKRQ1</u>
LI	Lead Pull to Destruction	Leads	-	-	-	-	1/24/0
PD	Auto Physical Dimensions	Cpk>1.67	-	-	-	3/30/0	-
SD	Surface Mount Solderability	Pb	-	-	-	1/15/0	1/15/0
SD	Surface Mount Solderability	Pb Free	-	-	-	1/15/0	1/15/0
UHAST	Unbiased HAST 130C/85%RH	96 Hours	1/77/0	-	3/231/0	1/77/0	-

⁻ Preconditioning was performed for Autoclave, Unbiased HAST, THB/Biased HAST, Temperature Cycle, Thermal Shock, and HTSL, as applicable

Quality and Environmental data is available at TI's external Web site: http://www.ti.com/

Green/Pb-free Status:

Qualified Pb-Free (SMT) and Green

Note (1): Two units failed Vio due to bad BI socket contact

⁻ The following are equivalent HTOL options based on an activation energy of 0.7eV: 125C/1k Hours, 140C/480 Hours, 150C/300 Hours, and 155C/240 Hours. The following are equivalent HTSL options based on an activation energy of 0.7eV: 150C/1k Hours, and 170C/170 Hours.

⁻ The following are equivalent HTSL options based on an activation energy of 0.7eV: 150C/1k Hours, and 170C/420 Hours
- The following are equivalent Temp Cycle options per JESD47: -55C/125C/700 Cycles and -65C/150C/500 Cycles

Qualification Report

Approve Date 11-May-2022

Qualification Results Data Displayed as: Number of lots / Total sample size / Total failed

Туре	Test Name / Condition	Duration	Qual Device: THS4131DGK	QBS Product Reference: THS4130DGK	QBS Product Reference: <u>THS4130ID</u>	QBS Process Reference: OPA2810IDGK	QBS Package Reference: <u>OPA2607QDGKRQ1</u>	QBS Package Reference: <u>OPA2991QDGKRQ1</u>
HTOL	Life Test, 125C	1000 Hours	-	-	-	3/231/0	-	-
HTOL	Life Test, 150C	408 Hours	-	-	-	-	1/77/0	3/231/1 (1)
ELFR	Early Life Failure Rate, 125C	48 Hours	-	-	-	3/3000/0	-	-
нвм	ESD - HBM	2500 V	-	-	1/3/0	3/9/0	1/3/0	-
CDM	ESD - CDM	1500 V	-	1/3/0	1/3/0	2/6/0	1/3/0	-
LU	Latch-up	Per JESD78	-	-	1/6/0	3/18/0	-	-
ED	Electrical Characterization	Per Datasheet Parameters	-	-	1/30/0	3/90/0	-	-
UHAST	Unbiased HAST 130C/85%RH	96 Hours	-	1/77/0	-	3/231/0	1/77/0	-
TC	Temperature Cycle, -65/150C	500 Cycles	-	1/77/0	-	3/231/0	-	3/231/0
AC	Autoclave 121C	96 Hours	-	-	-	-	-	3/231/0
HAST	Biased HAST, 130C/85%RH	192 hours	-	-	-	-	-	1/70/0
HAST	Biased HAST, 130C/85%RH	96 Hours	-	-	-	3/231/0	1/77/0	3/231/2 (1)
HTSL	High Temp Storage Bake 150C	1000 Hours	-	-	-	-	1/77/0	2/90/0
HTSL	High Temp Storage Bake 170C	420 Hours	-	-	-	3/231/0	-	-
LI	Lead Pull	Lead Pull	-	-	-	-	1/6/0	-

Туре	Test Name / Condition	Duration	Qual Device: <u>THS4131DGK</u>	QBS Product Reference: <u>THS4130DGK</u>	QBS Product Reference: <u>THS4130ID</u>	QBS Process Reference: <u>OPA2810IDGK</u>	QBS Package Reference: <u>OPA2607QDGKRQ1</u>	QBS Package Reference: <u>OPA2991QDGKRQ1</u>
LI	Lead Pull to Destruction	Leads	-	-	-	-	-	1/24/0
PD	Auto Physical Dimensions	Cpk>1.67	-	-	-	-	3/30/0	-
SD	Surface Mount Solderability	Pb	-	-	-	-	1/15/0	1/15/0
SD	Surface Mount Solderability	Pb Free	-	•	-	-	1/15/0	1/15/0
YLD	FTY and Bin Summary	-	1/Pass	-	-	-	-	-

⁻ Preconditioning was performed for Autoclave, Unbiased HAST, THB/Biased HAST, Temperature Cycle, Thermal Shock, and HTSL, as applicable

Quality and Environmental data is available at TI's external Web site: http://www.ti.com/

Green/Pb-free Status: Qualified Pb-Free (SMT) and Green

Note (1): Two units failed Vio due to bad BI socket contact

For questions regarding this notice, e-mails can be sent to the contact below or your local Field Sales Representative.

Location	E-Mail				
WW Change Management Team	PCN www admin_team@list.ti.com				

IMPORTANT NOTICE AND DISCLAIMER

TI PROVIDES TECHNICAL AND RELIABILITY DATA (INCLUDING DATASHEETS), DESIGN RESOURCES (INCLUDING REFERENCE DESIGNS), APPLICATION OR OTHER DESIGN ADVICE, WEB TOOLS, SAFETY INFORMATION, AND OTHER RESOURCES "AS IS" AND WITH ALL FAULTS, AND DISCLAIMS ALL WARRANTIES, EXPRESS AND IMPLIED, INCLUDING WITHOUT LIMITATION ANY IMPLIED WARRANTIES OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE OR NON-INFRINGEMENT OF THIRD PARTY INTELLECTUAL PROPERTY RIGHTS.

These resources are intended for skilled developers designing with TI products. You are solely responsible for (1) selecting the appropriate TI products for your application, (2) designing, validating and testing your

⁻ The following are equivalent HTOL options based on an activation energy of 0.7eV: 125C/1k Hours, 140C/480 Hours, 150C/300 Hours, and 155C/240 Hours

⁻ The following are equivalent HTSL options based on an activation energy of 0.7eV: 150C/1k Hours, and 170C/420 Hours
- The following are equivalent Temp Cycle options per JESD47: -55C/125C/700 Cycles and -65C/150C/500 Cycles

application, and (3) ensuring your application meets applicable standards, and any other safety, security, or other requirements. These resources are subject to change without notice. TI grants you permission to use these resources only for development of an application that uses the TI products described in the resource. Other reproduction and display of these resources is prohibited. No license is granted to any other TI intellectual property right or to any third party intellectual property right. TI disclaims responsibility for, and you will fully indemnify TI and its representatives against, any claims, damages, costs, losses, and liabilities arising out of your use of these resources.

TI's products are provided subject to TI's Terms of Sale (www.ti.com/legal/termsofsale.html) or other applicable terms available either on ti.com or provided in conjunction with such TI products. TI's provision of these resources does not expand or otherwise alter TI's applicable warranties or warranty disclaimers for TI products.